



DEBAL COATINGS NV INDUSTRIAL WOODCOATINGS

Houtlakken
Beitsen
Verduningen

Vernis bois
Teintes
Diluants

Holzlacke
Beize
Verdünnungen

Woodcoatings
Stains
Thinners

CIRANOVA® LACQUER - SYSTEM

PREPARATION

1

WOOD SANDING : GRAIN 40 - 60 - 80

WOOD FILLER (GEL OR WATER BASED)

FINE SANDING : GRAIN 100 - 120

SANDING BETWEEN COATS : GRAIN 150 - 180



PRIMING COAT

2

ECOFIX WOODLOOK
or AQUAFIX SEALER

1 coat



Don't sand the priming coat

FINITION / PROTECTION

3

AQUAFIX MONO matt, satin
or AQUAFIX PROJECT 2K matt, semi matt, glossy
or AQUAFIX MAGIC 2K very matt (gloss: <math><5^\circ</math>)
2 - 3 coats




It is recommended to consult the technical data sheet of the product for info about the application and specific properties.

MAINTENANCE

4

HARD FLOOR
FRESH



HARD FLOOR
CLEANER

HARD FLOOR
POLISH or
UNICARE X-MATT



It is recommended to consult the technical data sheet of the product for info about the application and specific properties.

Produced by Debal Coatings nv
Industrieweg 29 - 8800 Beveren Roeselare - Belgium
tel +32 (0)51 30 11 40 | fax +32 (0)51 31 26 48 | ciranova@ciranova.be
www.ciranova.eu